

Blocksil Fact Sheet

Reference	Blocksil
Purpose/Uses	Permanent Roof Membrane / Plant Room coating / Asbestos stabilizer. Potable water tank membrane.
Colour	RAL Colour range
Application	Apply by Brush - Powered Roller - Airless sprayer.
Volume Solids	100%
Recommended Film Thickness	1mm first coat and 1mm second coat
Coverage Rate	1 Sq meter per coat per 1 litre of product
Drying Time	Rain free - 3/4 hours. Thoroughly dry - 16 hours
Thinners/Brush wash	Gun wash or Xylene
Weight Per Litre	.98 at 20 deg C
Flash Point	Above 32 deg C
V.O.C	VOC Free
Finish	N/A
Application Temperature	+ 5 Deg C +60 Deg C
Approvals	BS 476:Part3 :1958, Fire and BS 6920 Water Quality
Surface Preparation	All surfaces must be clean and dry, remove any soiling by power wash etc.

FOR PROFESSIONAL USE ONLY